



# CMA Testing and Certification Laboratories

廠商會檢定中心

## TEST REPORT

Report No : AK029339-006


Date: 2008-08-20

Application No : LK223321

Applicant : ESPOMEGA S.A. DE C.V.  
CALLE PABLO A, GONZALEZ GARZA #820 PTE.,  
COL. CHEPEVERA, MONTERRY, NL 64030, MEXICO

Sample Description : One (1) set submitted sample of ten (10) gloves stated with Article No.: 99-200. \*\*\*

Sample Photo :



Date Received : 2008-08-04.

Test Period : 2008-08-04 to 2008-08-16.

Test details requested by the applicant :

1. Protective gloves against mechanical risks (Method : EN 388-2003)
  - a. Abrasion resistance (Section 6.1)

<u>Lowest cycles of breakdown</u>	<u>Performance level</u>
8000	4

Note : Performance level :

<u>Performance level</u>	<u>Cycles (minimum)</u>
1	100
2	500
3	2000
4	8000

For and on behalf of  
CMA Industrial Development Foundation Limited

Authorized Signature :

Wong Siu-Lam, Wilson  
Manager – Textile & Garment

Page 1 of 2

This document is issued subject to CMA Testing standard TERMS AND CONDITIONS, and shall not be reproduced except in full or with written approval by CMA Testing.

CMA Industrial Development Foundation Limited  
Room 1302, Yan Hing Centre, 9-13 Wong Chuk Yeung St., Fo Tan, Shatin, N.T., Hong Kong.

Tel: (852) 2698 8198 Fax: (852) 2695 4177 E-mail: info@cmatacl.com Web Site: http://www.cmatacl.com



# CMA Testing and Certification Laboratories

廠商會檢定中心

## TEST REPORT

Report No : AK029339-006

Date: 2008-08-20

Application No : LK223321

Test details requested by the applicant :

1. Protective gloves against mechanical risks (Method : EN 388-2003)
- b. Blade cut resistance (Section 6.2)

<u>Lowest average value (I)</u>	<u>Performance level</u>
3.6	2

Note : Performance level :

<u>Performance level</u>	<u>Index (I) (minimum)</u>
1	1.2
2	2.5
3	5.0
4	10.0
5	20.0

- c. Tearing strength [Tongue Tear - Single Rip] (Section 6.3)

<u>Lowest value (N)</u>	<u>Performance level</u>
64.7	3

Note : Performance level :

<u>Performance level</u>	<u>Newton (N) (minimum)</u>
1	10
2	25
3	50
4	75

- d. Puncture strength (Section 6.4)

<u>Lowest value (N)</u>	<u>Performance level</u>
147	3

Note : Performance level :

<u>Performance level</u>	<u>Newton (N) (minimum)</u>
1	20
2	60
3	100
4	150

Remark : N denotes Newton

\*\*\*\*\* End of Report \*\*\*\*\*